MULTIS 3 MULTI PURPOSE LITHIUM/CALCIUM GREASE Product Characteristic Sheet



APPLICATIONS	
Multi purpose grease General lubrication	 MULTIS 3 is a multipurpose grease for general lubrication under normal operating conditions and loads, formulated for lubrication of all kinds of universal applications in transport, agriculture and off road equipment, operating in wet, dusty and/or dry conditions. Lubrication of all kinds of bearings and joints when the temperature and loading conditions are normal. Pre-eminently suitable for passenger car, light truck and leisure vehicle applications.
Recommendation	• Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.
SPECIFICATIONS	• ISO 6743-9: L-XBCEA 3
	• DIN 51502: K3K -20
PROPERTIES	
Miscible Pumpability No harmful substances	 MULTIS 3 is miscible with most other conventional soap greases. Excellent mechanical stability avoiding ejection or loss of consistency during operation. Excellent pumpability due to the low temperature characteristics and smooth texture. Very good water resistance, even in a humid environment a sufficient lubricating film will be maintained. MULTIS 3 does not contain lead, or other heavy metals considered harmful to human health and the environment.

TOTAL UK Limited Lubricants Division Pottery Lane, Ferrybridge, West Yorks, WF11 8JY

MULTIS 3 07/03



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser.



	METHODS	UNITS	MULTIS 3
Soap/thickener		-	Lithium/ Calcium
NLGI grade	ASTM D 217/	-	3
	DIN 51 818		
Color	Visual	-	Glazy yellow
Appearance	Visual	-	Smooth
Operating temperature range		°C	-20 to 120
Penetration at 25°C	ASTM D 217/	0.1 mm	220-250
Felletiation at 25 C	DIN51 818		
	DIN 51 802/	rating	0-0
Anti-rust performance SKF- EMCOR	IP220/		
Anti-Tust performance SKF- ENCOR	NFT 60-135/		
	ISO 11007		
Dropping point	IP 396/	°C	>185
Dropping point	DIN ISO 2176		
	ASTM D 445/	mm²/s	120
Kinematic viscosity of the base oil at	DIN 51 562-1/		
40°C	ISO 3104/	111117/5	
	IP71		

Above characteristics are mean values given as an information.

TOTAL UK Limited Lubricants Division Pottery Lane, Ferrybridge, West Yorks, WF11 8JY

MULTIS 3 07/03



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser.